

Urochem 535

SINGLE COMPONENT HYBRID CONSTRUCTION SEALANT/ADHESIVE

DESCRIPTION

Urochem 535 is a thixotropic, VOC free, moisture curing, hybrid sealant/adhesive. It is a filled, moisture and oxidation resistant, mastic that exhibits excellent adhesion to cementitious, steel, wood, ceramic, aluminium, brick, and various other substrates. (Does not bond well to Stainless steel without a primer)

PRODUCT APPLICATION

- Urochem 535 can be used as a general joint sealer on low movement joints, as a crack filler on cementitious surfaces, as well as an adhesive on a wide range of substrates. It provides medium chemical, wear and corrosion resistance, while at the same time curing to a 35 Shore A hardness (+/- 5 Shore A). A degree of colour change with time is to be expected.
- ***It is not recommended for use in water retaining structures.***
- **Urochem 535** is overcoatable, however the coating will crack as it will not accommodate the same movement as the sealant.
- It is recommended that a compatibility test is done prior to application or painting.

SURFACE PREPARATION

All surfaces to be clean, sound, and dry, free of moisture, laitance, oils, and dust.

APPLICATION

- Ensure correct joint preparation before placing the sausage in the long barrel gun, cut end off sausage and fit the nozzle; trim the tip to suit the joint spacing to be filled before gunning the product into prepared joints.
- The adhesive may be smoothed and finish off with soapy water if required.

CLEANING

Clean all tools and equipment immediately after use with **Urochem 901**.

SAFETY

Contact with the skin should be avoided by wearing gloves, eye protection and protective clothing. In case of eye contact wash well and obtain medical advice.



Urochem Trading (Pty) Ltd

Unit XP2, AEL Industrial complex, Cnr Ecqip and Weighbridge
Modderfontein, Gauteng; 1645

(+27) 11 608 2073 • www.urochem.co.za

Urochem 535

SINGLE COMPONENT HYBRID CONSTRUCTION SEALANT/ADHESIVE

TYPICAL PROPERTIES

Mixing Ratio	Single component, use as supplied
Skin over time	Dependant on RH, temp & thickness
Practical Cure	+ 2mm per day dependant on RH & temp
Hardness	+35 Shore A
Tensile strength	2,0 - 4 Mpa
Elongation at break	>200 %
Colour	Neutral – Colours available on request
Density	1.5 Cured
Movement accommodation	15%
Shelf Life	12 Months
Application Temp.	5 - 35°C
Service Temp.	60° C Dry & 50° C Wet
Pack Size	600ml sausages
Cleaning	Urochem 901
Storage	Store in a cool dry place

The information supplied is believed to be reliable. As we do not have any control over the processing or application of the product, we cannot guarantee the results to be obtained. Users assume all risks and liability resulting from the use of this product and must confirm the suitability thereof by conducting their own tests. No guarantee is expressed or implied. Liability is limited to replacement of faulty material. Field service provided does not constitute supervisory responsibility.

FOR PROFESSIONAL USE ONLY



Urochem Trading (Pty) Ltd

Unit XP2, AEL Industrial complex, Cnr Ecqip and Weighbridge
Modderfontein, Gauteng; 1645

(+27) 11 608 2073 • www.urochem.co.za